

# SPEC REZ

Dissipating resin emulsion curing compound

## DESCRIPTION

A dissipating resin based emulsion curing compound for use on freshly finished horizontal and vertical concrete surfaces. SPEC REZ is formulated to provide an effective curing membrane that will begin to dissipate after exposure to sunlight, weathering and/or traffic.

## FEATURES / BENEFITS

- Ensures proper curing, resulting in stronger, more wear resistant concrete
- Helps minimize dusting
- Once film has dissipated, SPEC REZ is compatible with most paints, sealers, coating and floor covering adhesives

## SPECIFICATIONS/COMPLIANCES

- Formulated to comply with ASTM C-309, Types 1 and 1D, Class A & B
- AASHTO M-148, Type 1, Class A & B
- This product meets V.O.C. contents for Concrete Curing Compounds with a maximum V.O.C. content of 350 g/l.

## APPLICATION

Agitate thoroughly before use. Application equipment must be clean and free of foreign materials.

A spray application is the preferred method. Application temperatures above 40°F are recommended. Areas that are to be caulked should be masked. Do not pond or puddle. Coverage will vary depending on the texture and porosity of the concrete. Apply at a rate of 200-400 ft<sup>2</sup>/gal immediately after final trowel (or stripping of forms).

SPEC REZ is formulated as a dissipating type resin. The rate of dissipation is dependent upon climatic conditions, the rate of application and exposure to ultraviolet light. Under normal conditions, chemical and physical breakdown will start in 4-6 weeks.

Residual SPEC REZ may be removed with SpecChem Citrus Cleaner or any type of dry abrasive or sanding pad.

The use of SPEC REZ does not eliminate the need to properly prepare the surface in accordance with the written instructions for the application of secondary toppings or coatings.

Tools and equipment may be cleaned with warm water and soap.

## PACKAGING

55 gallon drums (208.2 L)  
5 gallon pails (18.9L)

## SHELF LIFE / STORAGE

Shelf life of SPEC REZ in the original tightly closed container is 1 year from the date of manufacture. Do not allow the accumulation of water, dirt or other contaminants.

## TYPICAL PERFORMANCE DATA

Moisture Retention (ASTM C-309) at 200 sq ft/gal (Kg/m <sup>2</sup> )	
Test Result	Required
0.39 Kg/m <sup>2</sup>	0.55 Kg/m <sup>2</sup>

## LIMITATIONS / PRECAUTIONS

- If surface is to be painted, sealed, topped, or otherwise treated after application, residual membrane should be removed.
- Do not apply at temperatures below 40°F (4°C).
- Keep from freezing.
- Do not dilute or alter in any way
- Always follow subsequent coating manufacturers' recommendations for surface preparation.
- All resin cures turn yellow while they are dissipating (oxidizing). This is a normal part of the dissipation process.
- Use with adequate ventilation
- Keep out of the reach of children
- In case of ingestion, CALL A PHYSICIAN immediately. DO NOT induce vomiting.
- Can cause skin irritation upon contact, especially prolonged or repeated. If skin contact occurs, wash immediately with soap and water and seek medical help as needed.
- If eye contact occurs, flush immediately with clean water and seek medical help as needed.
- Read MSDS before using product.

## TECHNICAL SERVICES

For assistance, contact technical services at:  
866-791-8700 913-371-8700  
www.specchemllc.com



# WARRANTY

## **NOTICE-READ CAREFULLY**

### **CONDITIONS OF SALE**

SpecChem offers this product for sale subject to and limited by the warranty which may only be varied by written agreement of a duly authorized corporate officer of SpecChem. No other representative of or for SpecChem is authorized to grant any warranty or to waive limitation of liability set forth below.

### **WARRANTY LIMITATION**

SpecChem warrants this product to be free of manufacturing defects. If the product when purchased was defective and was within use period indicated on container or carton, when used, SpecChem will replace the defective product with new product without charge to the purchaser. SpecChem makes no other warranty, either expressed or implied, concerning this product. There is no warranty of merchantability. NO CLAIM OF ANY KIND SHALL BE GREATER THAN THE PURCHASE PRICE OF THE PRODUCT IN RESPECT OF WHICH DAMAGES ARE CLAIMED.

### **INHERENT RISK**

Purchaser assumes all risk associated with the use or application of the product.

